



ThinFlex



ThinFlex Corporation

No. 8, Luke 2nd.Rd., Luzhu Dist., Kaohsiung City, 821, Taiwan, R.O.C. (Kaohsiung Science Park) Tel: +886-7-6955236 Fax: +886-7-6955539 http://www.thinflex.com.tw e-mail: service@thinflex.com.tw

ThinFlex-AR, AR-1003RD-J3F Adhesiveless Double Sided Copper Clad Laminate (Halogen Free)

ThinFlex-AR, AR-1003RD-J3F is an adhesiveless double-sided (D/S) copper clad laminate, using ARISAWA TPI film and laminated with RA copper foil on both sides. The AR-1003RD-J3F adhesiveless D/S composites are designed for a wide variety of flexible circuit applications which require advanced material performance and high reliability.

1. Product Characteristics:

- * Excellent dimensional stability
- * Excellent flexibility
- * Excellent etching capability
- * Excellent flame resistance
- * Excellent chemical resistance
- * Excellent thermal, mechanical, and electrical properties
- * Low moisture absorption

2. Specifications:

AR - 10 03 R D-J3F

Product	Thickness of PI	Thickness of Cu	Cu Type	Structure	Cu Supplier
AR-type FCCL	10 : 1.0 mil	03 : 0.3 oz	RA	D: D/S	Nippon mining & metals
Product Size	W: 250/500 ± 1mm; L: 400~700 ± 2mm (sheet type) W: 250/500 ± 1mm; L: 100 +2/-0m (roll type)				

* Other product size is also available on customer's demand.



ThinFlex

Distributed by:
ventec
INTERNATIONAL GROUP
騰輝電子

ThinFlex Corporation

No. 8, Luke 2nd.Rd., Luzhu Dist., Kaohsiung City, 821, Taiwan, R.O.C.
(Kaohsiung Science Park)
Tel: +886-7-6955236 Fax: +886-7-6955539
http://www.thinflex.com.tw
e-mail: service@thinflex.com.tw

3. Construction:

Copper foil
Polyimide film
Copper foil

4. Properties:

Test item	Unit	AR-1003RD-J3F	Test Method	
Peel Strength				
As Received	Kgf/cm	≥0.6	IPC-TM650 2.4.9	
Solder Float	Kgf/cm	≥0.6	IPC-TM650 2.4.9	
After Temp. Cycling	Kgf/cm	≥0.6	IPC-TM650 2.4.9	
Chemical Resistance	Kgf/cm	≥0.6	IPC-TM650 2.3.2	
Tensile Strength (Base Film)	Kg/mm ²	≥24	IPC-TM-650 2.4.19	
Elongation (Base Film)	%	≥40	IPC-TM-650 2.4.19	
Tensile Modulus (Base Film)	Kg/mm ²	≥450	ASTM D882	
Initial Tear Strength (Base Film)	g	≥600	IPC-TM-650 2.4.16	
Propagation Tear Strength (Base Film)	g	≥10	IPC-TM-650 2.4.17.1	
Flexural Endurance, MIT				
M.D.	Cycles	≥800	JIS-C 6471, 0.8mmR, 0.5kg	
T.D.	Cycles	≥800	JIS-C 6471, 0.8mmR, 0.5kg	
Electrical Properties				
Surface Resistance	Ω	~10 ¹¹	IPC-TM650 2.5.17	
Volume Resistance	Ω-cm	~10 ¹²	IPC-TM650 2.5.17	
Insulation Resistance	Ω	~10 ⁹	IPC-TM650 2.6.3.2	
Dielectric Strength	kV/mil	6.5	ASTM-D149	
Dielectric Constant	-	3.3	IPC-TM650 2.5.5.3	
Dissipation factor	-	0.01	IPC-TM650 2.5.5.3	
Physical and Thermal Properties				
Dimensional Stability	M.D.	%	-0.1~0.1	IPC-TM650 2.2.4C
	T.D.	%	-0.1~0.1	IPC-TM650 2.2.4C
CTE	ppm/°C	26	ThinFlex	
T _g	°C	330	ThinFlex	
Solder Float	10sec at 288°C (550°F)	-	Pass	IPC-TM650 2.4.13
Moisture Absorption	%	1.1	IPC-TM650 2.6.2	
Chemical Resistance	-	Pass	IPC-TM650 2.3.2	
Thickness tolerance	um	49±10%	ThinFlex	
UL Flame Class	-	VTM-0	UL94	

* Above data are typical values, and are not guaranteed values.



Distributed by:
ventec
INTERNATIONAL GROUP
騰輝電子

ThinFlex Corporation

No. 8, Luke 2nd.Rd., Luzhu Dist., Kaohsiung City, 821, Taiwan, R.O.C.
(Kaohsiung Science Park)
Tel: +886-7-6955236 Fax: +886-7-6955539
<http://www.thinflex.com.tw>
e-mail: service@thinflex.com.tw

5. Storage:

ThinFlex-AR, AR-1003RD-J3F will meet its shelf-life for at least 12 months after arrival at purchaser's factory with original package, stored at temperature of 25°C or less and relative humidity of 70% or less. The product is no need to be kept in the refrigeration.

Note: The information and data contained in this technical literature is believed to be accurate and is offered in good faith for the benefit of the user. The user should make his own tests to verify the suitability of this product for any application before its use. All data are typical values only and subject to change without notice.

ThinFlex Corporation

No.8, Luke 2nd Rd., Luzhu Dist., Kaohsiung City 821, Taiwan, R.O.C. (Kaohsiung Science Park)
Tel: +886-7-6955236 Fax: +886-7-6955539
<http://www.thinflex.com.tw>
e-mail: service@thinflex.com.tw