



ThinFlex

Distributed by:
ventec
INTERNATIONAL GROUP
騰輝電子

ThinFlex Corporation

No. 8, Luke 2nd.Rd., Luzhu Dist., Kaohsiung City, 821, Taiwan, R.O.C.
(Kaohsiung Science Park)
Tel: +886-7-6955236 Fax: +886-7-6955539
http://www.thinflex.com.tw
e-mail: service@thinflex.com.tw

ThinFlex A-2010ED

Adhesiveless Double Sided Copper Clad Laminate

(Halogen Free)

ThinFlex A-2010ED is an adhesiveless double-sided (D/S) copper clad laminate, using UBE TPI film and laminated with ED copper foil on both sides. ThinFlex A-2010ED adhesiveless D/S composites are designed for a wide variety of flexible circuit applications which require advanced material performance, temperature resistance, fine pitch, and high reliability.

1. Product Characteristics:

- * Excellent dimensional stability
- * Excellent flexibility
- * Finer line etching capability
- * Low moisture absorption
- * Excellent flammability (Flame class UL 94V-0; UL File No. E219724)
- * Excellent chemical resistance
- * Excellent thermal, mechanical, and electrical properties

2. Specifications:

A - 20 10 E D

Product A : D/S FCCL	Thickness of PI 20 : 2.0 mil	Thickness of Cu 10 : 1.0oz	Cu Type E : ED	Structure Double-sided
Supply Size	W: 250/500 ± 1mm; L: 400~700 ± 2mm (sheet type) W: 250/500 ± 1mm; L: 50 +2/-0m (roll type)			

***Other thicknesses and dimensions are available on customers' demand.**



ThinFlex

Distributed by:
ventec
INTERNATIONAL GROUP
騰輝電子

ThinFlex Corporation

No. 8, Luke 2nd.Rd., Luzhu Dist., Kaohsiung City, 821, Taiwan, R.O.C.
(Kaohsiung Science Park)
Tel: +886-7-6955236 Fax: +886-7-6955539
http://www.thinflex.com.tw
e-mail: service@thinflex.com.tw

3. Construction:

Copper foil
Polyimide film
Copper foil

4. Properties:

Test item	Unit	A-2010ED	Test Method
Peel Strength			
As Received	Kgf/cm	≥ 1.0	IPC-TM650 2.4.9 B
Solder Float	Kgf/cm	≥ 1.0	IPC-TM650 2.4.13 B
After Temp. Cycling	Kgf/cm	≥ 1.0	IPC-TM650 2.4.9
Chemical Resistance	Kgf/cm	≥ 1.0	IPC-TM650 2.3.2
Tensile Strength (Base Film)	Kg/mm ²	30	IPC-TM-650 2.4.19
Elongation (Base Film)	%	35	IPC-TM-650 2.4.19
Tensile Modulus (Base Film)	Kg/mm ²	430	ASTM D882
Initial Tear Strength (Base Film)	g	1940	IPC-TM-650 2.4.16
Propagation Tear Strength (Base Film)	g	30	IPC-TM-650 2.4.17.1
Flexural Endurance, MIT			
M.D.	Cycles	NA	JIS-C 6471, 0.8mmR, 0.5kg
T.D.	Cycles	NA	JIS-C 6471, 0.8mmR, 0.5kg
Electrical Properties			
Surface Resistance	Ω	~10 ¹¹	IPC-TM650 2.5.17
Volume Resistance	Ω-cm	~10 ¹²	IPC-TM650 2.5.17
Insulation Resistance	Ω	~10 ⁹	IPC-TM650 2.6.3.2
Dielectric Strength	kV/mil	6.9	ASTM-D149
Dielectric Constant	-	3.3	IPC-TM650 2.5.5.3
Dissipation factor	-	0.002	IPC-TM650 2.5.5.3
Physical and Thermal Properties			
Dimensional Stability M.D.	%	-0.1~0.1	IPC-TM650 2.2.4C
Dimensional Stability T.D.	%	-0.1~0.1	IPC-TM650 2.2.4C
CTE	ppm/°C	19.3	ThinFlex
T _g	°C	350	ThinFlex
Solder Float	10sec at 288°C (550°F)	-	Pass IPC-TM650 2.4.13
Moisture Absorption Test	%	1.1	IPC-TM650 2.6.2
Chemical Resistance-single	-	Pass	IPC-TM650 2.3.2
Thickness tolerance	um	120±10%	ThinFlex
UL Flame Class	-	94V-0	UL

* Above data are typical values, and are not guaranteed values.



ThinFlex

Distributed by:
ventec
INTERNATIONAL GROUP
騰輝電子



ThinFlex Corporation

No. 8, Luke 2nd.Rd., Luzhu Dist., Kaohsiung City, 821, Taiwan, R.O.C.
(Kaohsiung Science Park)
Tel: +886-7-6955236 Fax: +886-7-6955539
<http://www.thinflex.com.tw>
e-mail: service@thinflex.com.tw

5. Storage:

ThinFlex A-2010ED will meet its shelf-life for at least 12 months after arrival at the user's factory when stored in the original packaging at temperatures of below 25°C and below 70% humidity. The products do not need refrigeration and should not be frozen.

Note: The information and data contained in this technical literature is believed to be accurate and is offered in good faith for the benefit of the user. The user should make his own tests to verify the suitability of this product for any application before its use. All data are typical values only and subject to change without notice.

ThinFlex Corporation

No.8, Luke 2nd Rd., Luzhu Dist., Kaohsiung City 821, Taiwan, R.O.C. (Kaohsiung Science Park)
Tel: +886-7-6955236 Fax: +886-7-6955539
<http://www.thinflex.com.tw>
e-mail: service@thinflex.com.tw