



ThinFlex



ThinFlex Corporation

No. 8, Luke 2nd.Rd., Luzhu Dist., Kaohsiung City, 821, Taiwan, R.O.C. (Kaohsiung Science Park) Tel: +886-7-6955236 Fax: +886-7-6955539 http://www.thinflex.com.tw e-mail: service@thinflex.com.tw

ThinFlex W-1010ED-N4 Adhesiveless Double Sided Copper Clad Laminate (Halogen Free)

IPC Designation IPC-4204/11

ThinFlex W-1010ED-N4 is an adhesiveless double-sided (D/S) copper clad laminate, using ThinFlex TPI film and laminated with ED copper foil on both sides. ThinFlex W-1010ED-N3 adhesiveless D/S composites are designed for a wide variety of flexible circuit applications which require advanced material performance, temperature resistance, fine pitch, and high reliability.

1. Product Characteristics:

- * Excellent dimensional stability
- * Excellent flexibility
- * Finer line etching capability
- * Low moisture absorption
- * Excellent flammability
- * Excellent chemical resistance
- * Excellent thermal, mechanical, and electrical properties

2. Specifications:

W- 10 10 E D-N4

Product	Thickness of PI	Thickness of Cu	Cu Type	Structure	Cu Supplier
W-type FCCL	10: 1.0 mil	10 : 1 Oz.	E : ED	D: D/S	N: Nanya 4 : Model
Supply Size	W: 250/500 ± 1mm; L: 400~700 ± 2mm (sheet type) W: 250/500 ± 1mm; L: 100 +2/-0m (roll type)				

*Other thicknesses and dimensions are available on customers' demand.



ThinFlex

Distributed by:
ventec
INTERNATIONAL GROUP
騰輝電子

ThinFlex Corporation

No. 8, Luke 2nd.Rd., Luzhu Dist., Kaohsiung City, 821, Taiwan, R.O.C.
(Kaohsiung Science Park)
Tel: +886-7-6955236 Fax: +886-7-6955539
http://www.thinflex.com.tw
e-mail: service@thinflex.com.tw

3. Construction:

Copper foil
Polyimide film
Copper foil

4. Properties:

IPC Designation IPC-4204/11

Test item	Unit	W-1010ED-N4	Test Method	
Peel Strength				
As Received	Kgf/cm	≥ 0.8	IPC-TM650 2.4.9 B	
Solder Float	Kgf/cm	≥ 0.8	IPC-TM650 2.4.13 B	
After Temp. Cycling	Kgf/cm	≥ 0.8	IPC-TM650 2.4.9	
Chemical Resistance	Kgf/cm	≥ 0.8	IPC-TM650 2.3.2	
Tensile Strength (Base Film)	Kg/mm ²	24	IPC-TM-650 2.4.19	
Elongation (Base Film)	%	25	IPC-TM-650 2.4.19	
Tensile Modulus (Base Film)	Kg/mm ²	500	ASTM D882	
Initial Tear Strength (Base Film)	g	720	IPC-TM-650 2.4.16	
Propagation Tear Strength (Base Film)	g	13	IPC-TM-650 2.4.17.1	
Flexural Endurance, MIT				
M.D.	Cycles	≥ 200	JIS-C 6471, 0.8mmR, 0.5kg	
T.D.	Cycles	≥ 200	JIS-C 6471, 0.8mmR, 0.5kg	
Electrical Properties				
Surface Resistance	Ω	≥ 1.0×10 ¹¹	IPC-TM650 2.5.17	
Volume Resistance	Ω-cm	≥ 1.0×10 ¹²	IPC-TM650 2.5.17	
Insulation Resistance	Ω	≥ 1.0×10 ⁹	IPC-TM650 2.6.3.2	
Dielectric Strength	kV/mil	5.5	ASTM-D149	
Dielectric Constant	-	3.3	IPC-TM650 2.5.5.3	
Dissipation factor	-	0.01	IPC-TM650 2.5.5.3	
Physical and Thermal Properties				
Dimensional Stability	M.D.	%	-0.1~-0.1	IPC-TM650 2.2.4C
	T.D.	%	-0.1~-0.1	IPC-TM650 2.2.4C
CTE	ppm/°C	24	ThinFlex	
T _g	°C	350	ThinFlex	
Solder Float	30sec at 288°C (550°F)	-	Pass	IPC-TM650 2.4.13
Moisture Absorption Test	%	1.1	IPC-TM650 2.6.2	
Chemical Resistance-single	-	Pass	IPC-TM650 2.3.2	
Thickness tolerance	um	95±10%	ThinFlex	
UL Flame Class	-	94V-0	UL	

* Above data are typical values, and are not guaranteed values.



ThinFlex

Distributed by:
ventec
INTERNATIONAL GROUP
騰輝電子



ThinFlex Corporation

No. 8, Luke 2nd.Rd., Luzhu Dist., Kaohsiung City, 821, Taiwan, R.O.C.
(Kaohsiung Science Park)
Tel: +886-7-6955236 Fax: +886-7-6955539
<http://www.thinflex.com.tw>
e-mail: service@thinflex.com.tw

5. Storage:

ThinFlex W-1010ED-N4 will meet its shelf-life for at least 12 months after arrival at the user's factory when stored in the original packaging at temperatures of below 25°C and below 70% humidity. The products do not need refrigeration and should not be frozen.

Note: The information and data contained in this technical literature is believed to be accurate and is offered in good faith for the benefit of the user. The user should make his own tests to verify the suitability of this product for any application before its use. All data are typical values only and subject to change without notice.

ThinFlex Corporation

No.8, Luke 2nd Rd., Luzhu Dist., Kaohsiung City 821, Taiwan, R.O.C. (Kaohsiung Science Park)
Tel: +886-7-6955236 Fax: +886-7-6955539
<http://www.thinflex.com.tw>
e-mail: service@thinflex.com.tw